









CARTRIDGE HEATERS LEAD ENDSEAL OPTIONS

Endseal Type	Maximum Temperature	Moisture Protection	Contamination	Mechanical Strength	Vibration Resistance
 Ceramic Endpiece	2500 °F / 1371 °C	Poor	Poor	Excellent	Excellent
 Teflon Endpiece	300 °F / 149 °C	Excellent	Excellent	Very Good	Excellent
 Lava Seal	3000 °F / 1649 °C	Poor	Good	Good	Poor
 Mica Seal	2500 °F / 1371 °C	Poor	Good	Average	Average
 Cement Potting	1800 °F / 982 °C	Poor	Fair	Good	Poor
 Epoxy Potting	265 °F / 129 °C	Good	Good	Excellent	Excellent
 EpoxyLite Potting	650°F / 343 °C	Fair	Very Good	Very Good	Excellent
 Silicone Rubber	500 °F / 260 °C	Excellent	Excellent	Fair	Excellent